

# STATUS POLYPRIMER

## ECOLOGICAL MULTI-PURPOSE PRIMER



### DESCRIPTION

**STATUS POLYPRIMER** is an ecological multi-purpose water soluble primer. It is the ideal substrate for wooden surfaces before they are painted with water based varnish. It is also suitable for plaster, gypsum board, hard PVC, polyester and glass. It is odourless and it

is user and environmental friendly. **STATUS POLYPRIMER** offers exceptional coverage, is softly worked and wonderfully spread, thus securing strong adhesion and an excellent final result.

### APPLICATION FIELDS

Suitable for preparation of:

- Wooden surfaces before they are painted with water based varnish.
- New surfaces, such as plaster, gypsum board, hard PVC, polyester and glass.

### ADVANTAGES – CHARACTERISTICS

- Ecological product, environmental friendly, without solvents.
- Odourless
- Strong adhesion.
- Suitable for application on several kinds of substrates.
- Perfect coverage.
- Worked excellently.
- Exceptional result.

### SUBSTRATE PREPARATION

The surface should necessarily be clean, dry, rigid and free from dust, grease and rust for good adhesion. Remove all detached or peeled old paints. Metals are cleaned with **LS-735 SOLVENT** or Acetone.

Surfaces from hard PVC, polyester or glass are washed with water and detergent. In case of fresh plaster or cement, it should be left to dry in depth for at least 1 month before the application of the paint.

### APPLICATION

Mix well the content of the container before use, dilute properly and apply 1-2 layers of paint. After application, close the container tightly to maintain in good condition for future use. It can be stored in a tightly closed container for a long time as long as it has not been diluted. On absorbent or very rough surfaces the material is applied with sprayer. In this way,

the material can penetrate everywhere very fast and the application rate remains low. During application make sure that the material is absorbed and not just forming a thin layer on the surface. If a second layer is required, apply at least 6 hours after the first. Recoating time is extended under conditions of increased atmospheric humidity.

## DRYING

Touch dry after 2-3 hours.

## RECOATING

Recoat after 6 hours. Drying times refer to normal environmental conditions (25°C, humidity 60%). Any difference in environmental temperature and humidity could affect the above times.

## SHADES

Available in white.

## APPLICATION RATE

10-12 m<sup>2</sup>/lt, depending on the feel and absorbability of the surface.

## APPLICATION TOOLS

Brush, roller or spray gun.

## CLEANING OF TOOLS

Immediately after use empty all the paint into the container and clean the tools with hot water and soap. Do not pour the washing liquids on the ground.

## PACKAGING

Available in plastic containers of 0.75 lt and 2.5 lt.

## STORAGE

After application close the container tightly to preserve in good condition for future use. It can be stored in tightly closed containers for a long time as long as it has not been diluted. Store in cool and dry places. Protect from sun and frost.

## VOLATILE ORGANIC COMPOUNDS (VOC)

- Maximum permissible VOC content (Directive 2004/42/EC) for “One-pack performance coatings” (WB):100 gr/lt.
- Maximum VOC content of product ready for use: 95 gr/lt.

## APPLICATION TEMPERATURE

Avoid painting at temperatures lower than 10°C or before rain. During application the surface should not be directly exposed to solar radiation.

Adverse conditions during or shortly after application could affect the final properties of the product.

# STATUS POLYPRIMER

## ECOLOGICAL MULTI-PURPOSE PRIMER



### PRECAUTIONS

For information about safe use, storage and disposal of the product read the information on the label and in the most recent MSDS of the product, which is available upon request to the professionals.

The remains of the paints should not be disposed of together with domestic waste. Ask for advice from the local government with regard to the disposal and removal of waste.

Poisoning Centre Tel. No.: +30 210 77.93.777

TECHNICAL CHARACTERISTICS	UNITS	STANDARD	VALUE
Density (20°C)	(g/ml)	EN ISO 2811.01-02	1.03 ± 0.05
Viscosity	(cps)	Brookfield	2,500 ± 400
pH		ISO 976-96	8-8.7
Dilution with water for application with	brush	-	5-10
	gun		15-20

**Note:** The measurements were taken in laboratory environment under a temperature of +23°C, Relative Humidity 50 % and without ventilation. They may vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation and absorbability of the substrate.